



The 28<sup>th</sup> Iranian Conference on  
Optics and Photonics (ICOP 2022),  
and the 14<sup>th</sup> Iranian Conference on  
Photonics Engineering and  
Technology (ICPET 2022).

Shahid Chamran  
University of Ahvaz,  
Khuzestan, Iran,  
Feb. 1-3, 2022



## بررسی تأثیر ساختار ناهمگون و اندروالسی فسفرن آبی-دی کالکوژنید فلزات واسط ( $\text{MoS}_2, \text{WS}_2, \text{MoSe}_2, \text{WSe}_2$ ) بر افزایش حساسیت زیست حسگر تشدید پلاسمون سطحی

امیر دوامی<sup>۱</sup>، محمد هادی شاهرخ آبادی<sup>۱\*</sup>

<sup>۱</sup>دانشکده مهندسی برق و کامپیوتر، دانشگاه حکیم سبزواری، سبزوار، ایران

چکیده- در این مقاله تأثیر ساختار ناهمگون و اندروالسی فسفرن آبی-دی کالکوژنید فلزات واسط (دی سلنید تنگستن، دی سولفید تنگستن، دی سلنید مولیبدن، دی سولفید مولیبدن) با ضخامت های مختلف در ساختار زیست حسگر تشدید پلاسمون سطحی (SPR) در نرم افزار لومریکال شبیه سازی و بررسی شده است. ساختار پیشنهادی بر اساس ساختار کرشمن می باشد که در آن از منشور باجنس  $\text{BK}_7$ ، لایه ی طلای  $30$  نانومتری و لایه فسفرن آبی/دی کالکوژنید فلزات واسط استفاده شده است. مشاهده می شود که حداقل مقدار بازتاب برای  $6$  لایه فسفرن آبی/دی سلنید تنگستن و لایه  $30$  نانومتری طلا رخ می دهد که حساسیت در این ساختار برای  $\Delta n = 0.009$  برابر  $151/88^\circ/\text{RIU}$  و دقت تشخیص نیز برابر  $0.087$  است.

کلیدواژه- بازتاب، تشدید پلاسمون سطحی، حساسیت، زیست حسگر، ساختار ناهمگون و اندروالسی فسفرن آبی/دی کالکوژنید فلزات واسط.

## Investigating the Effect of Blue Phosphorene-MX<sub>2</sub> ( $\text{MoS}_2, \text{WS}_2, \text{MoSe}_2, \text{WSe}_2$ ) Vander Waals Heterostructure on the Enhancements Sensitivity of an SPR- Biosensor

Amir Davami<sup>1</sup>, Mohammad Hadi Shahrokh Abadi<sup>1\*</sup>

<sup>1</sup> Electrical and Computer Engineering Faculty, Hakim Sabzevari University, Sabzevar, Iran

Emails: ad.davami@gmail.com , mhshahrokh@ieee.

**Abstract-** In this paper, the effect of Blue Phosphorene - transition metal dichalcogenides (Blue P-TMDs) vander Waals (vdW) Heterostructure layer with different thickness on the structure of surface plasmon resonance (SPR) biosensor in a Lumerical software environment is simulated and investigated. The main structure is based on the structure of Kretschmann and the use of the  $\text{BK}_7$  prism, the gold (Au) layer, and the end layer of Blue P-TMDs or Blue P-MX<sub>2</sub> ( $\text{MoS}_2, \text{MoSe}_2, \text{WS}_2, \text{WSe}_2$ ). It was observed that the minimum reflectance of  $0.002$  is achieved for Au ( $30\text{nm}$ ) / Blue P- $\text{WSe}_2$  (1-Layer). The combination also yields a sensitivity of  $151.88^\circ/\text{RIU}$  for  $\Delta n = 0.009$  with a great detection accuracy of  $0.087$ .

**Keywords:** Biosensor, Blue P-TMDs vdW heterostructure, Reflectance Surface Plasmon Resonance, Sensitivity.

## 1. Introduction

Surface plasmon resonance sensors are one of the types of optical sensors which measure various biologicals and chemical parameters based on the interaction between the sample medium and the sensor surface.[1], [2] To excite surface plasmons at the metal-dielectric interface, the electrons of the metal conduction band must be able to resonance with input light on the surface at a given wavelength.[3]

In surface plasmon resonance based biosensors, gold or silver is generally coated directly onto the prism to separate the sensor medium from the prism. Biomolecules have a low capacity to interact with gold, which reduces the sensitivity of the sensor. To resolve this problem, in recent studies of biosensor structure, one or more layers of graphene have been used because of the high surface-volume ratio, high electrical mobility and stability of the atomic structure.[4] However, it does not act as a semiconductor due to insufficient of bandgap in its electronic structure.[5] This deficiency prevents its use in numerous applications, including optoelectronics. Transitional metal dichalcogenides (TMDs), another important component of the 2D material family, have also aroused scientists' interest. The most common TMDs are molybdenum disulfide (MoS<sub>2</sub>), Tungsten disulfide (WS<sub>2</sub>), Molybdenum diselenide (MoSe<sub>2</sub>) and Tungsten diselenide (WSe<sub>2</sub>). They have a perceptible band gap, allowing the conversion of electrons into light photons and resulting in extraordinary on/off ratios. [6]

Today, other 2D materials such as Black phosphorene (BlackP) and Blue phosphorene (BlueP) are being investigated. However, BlackP and BlueP are easily degraded in ambient air.[7] BlueP has the same hexagonal crystalline structure and lattice parameter as TMDs, such as MoS<sub>2</sub>, MoSe<sub>2</sub>, WS<sub>2</sub> and WSe<sub>2</sub>. To avoid the BlueP of external agents, a combination of 2D materials

with BlueP is developed, resulting in the possibility of vander Waals (vdW) heterostructure. Moreover, this heterostructure plays an important role in the improvement of the optical and electronic stability properties of materials compared to their 2D shapes.[8]

In the present article, a structure consisting of different layers of Blue Phosphorene-TMDs (MoS<sub>2</sub>, MoSe<sub>2</sub>, WS<sub>2</sub>, WSe<sub>2</sub>) vander Waals (vdW) Heterostructure on an Au layer has been proposed. The structure formed as an SPR biosensor at 633 nm incident light. The various structures were then simulated in the Lumerical environment and modifications of the refractive index were investigated and compared.

## 2. The Proposed SPR-Biosensor Structure

In this paper, we use the 4-layer Krishmann structure, including the prism, gold (Au) layer, Blue P-TMDs vdW heterostructure, and sample environment, respectively. The physical properties of the different materials used for the simulation are presented in Table I.

Table I. Refractive index and thickness different layers.

Layer	Refractive Index	Thickness
Prism[8]	1.515	-----
Au[8]	0.185+3.423i	30 nm
BP-MoS <sub>2</sub> [9]	2.81+0.32i	0.75 nm
BP-WS <sub>2</sub> [9]	2.48+0.17i	0.75 nm
BP-MoSe <sub>2</sub> [9]	2.77+0.30i	0.75 nm
BP-WSe <sub>2</sub> [9]	2.0+0.14i	0.75 nm

Important parameters in the surface plasmon resonance sensor that reflect the performance of this sensor include: Sensitivity(S); Indicates the rate of change of sensor output to the measured characteristic changes, expressed as follows.

$$S = \frac{\Delta \theta_{SPR}}{\Delta n} \quad (1)$$

Detection accuracy(D.A)Indicates the proximity of the measured characteristic to its true value, and It is mentioned in relation 2.

$$D.A = \frac{\Delta\theta_{SPR}}{FWHM} \quad (2)$$

The quality factor ; It is expressed by Equation 3. [10]

$$Q = \frac{S}{FWHM} \quad (3)$$

## 3. Results and Discussion

The aims of this article is to investigate a new detection configuration with using layers of Blue P-TMDs(MoS<sub>2</sub>,WS<sub>2</sub>,MoSe<sub>2</sub>,WSe<sub>2</sub>) on a thin layer of gold to improve the capacity of the light absorption of the SPR-biosensor and to further enhance its sensitivity.As shown in Fig.1, we first examine the structure with the Au/Blue P-TMDs(1L) sensitive layer and compare it with the results of the gold monolayer at the top of the prism.




Fig. 1: Illustration of the SPR-biosensor structure

As can be seen in Fig. 1, the minimum reflectance( $R_{min}$ ) in the structure with the Au layer and the thickness of 30 nm is 0.247 and by adding an additional monolayer of Blue P-TMDs(MoS<sub>2</sub>,WS<sub>2</sub>,MoSe<sub>2</sub>,WSe<sub>2</sub>) on Au a ~30% reduction in  $R_{min}$  occurs in 0.174 and an approximate difference in SPR angle is  $\Delta\theta \approx 10^\circ$ . This is achieved in the best conditions for the Blue P-WSe<sub>2</sub> layer. By retaining the Au layer thickness

at 30 nm, the impact of additional layer of Blue P-WSe<sub>2</sub> on the minimum reflectance of the Au(30 nm)/Blue P-WSe<sub>2</sub> configuration was also investigated and compared. As shown in Fig. 2, when the thickness of Blue P-WSe<sub>2</sub> layer grows the lowest reflectance approaches 0.02 for Au(30 nm)/Blue P-WSe<sub>2</sub>(8L). Table II, lists the minimum reflectances corresponding to the angles of occurrence for the setup simulation at different thickness of Blue P-WSe<sub>2</sub> layers in Au30 / Blue P-WSe<sub>2</sub> configurations in  $n = 1.33$  environment.




Fig. 2: The reflection spectra for different thickness of Blue P-WSe<sub>2</sub> layers in Au(30 nm)/Blue P-WSe<sub>2</sub>

Table II. Resonance angle ( $\theta^o$ ) and  $R_{min}$  values for different thickness of Blue P/WSe<sub>2</sub> layers in Au30 / Blue P-WSe<sub>2</sub> configurations in  $n = 1.33$  environment.

Layer number of Blue P/WSe <sub>2</sub>	Resonance Angle( $\theta^o$ )	Minimum Reflectance( $R_{min}$ )
1	71,90	0,247
2	73,32	0,142
3	73,32	0,090
4	74,69	0,038
5	76,06	0,017
6	77,42	0,0020
7	77,42	0,0028
8	78,79	0,0022

From the results of Fig. 1 and 2 we can see that the minimum reflectance happens at 0.02. This means that the combination Au(30 nm)/BP-WSe<sub>2</sub>(8L) is the most optimal structure among the available configurations. By modifying the

medium to  $n = 1.339$ , the sensor's sensitivity and the spectral response of the Au(30 nm)/BP- $\text{WSe}_2$ (1L) structure are investigated. Fig. 3 indicates the response of the spectral reflection to various environments. Sensitivity, can now be determined using the above mentioned Eq. (1) and the details of Fig. 3 for replies to  $n = 1.330$  and  $n = 1.339$ , which are listed in Table III based on Fig. 3 information. The results of another investigation into Au(30 nm)/G(1L) are also presented for comparison. [11]




Fig. 3: The reflection spectra for Au(30 nm)/BP- $\text{WSe}_2$ (1L) configuration at watery ( $n = 1.330$ ) and analyte ( $n = 1.339$ ) representing.

Table III. The sensitivity ( $S$ ), detection accuracy ( $DA$ ), and quality ( $Q$ ) of the proposed Au(30 nm)/BP- $\text{WSe}_2$ (1L) SPR-biosensor vurses work in [28] for  $n = 1.339$  medium.

SPR-Biosensor Configuration	Au(30 nm)/BP- $\text{WSe}_2$ (1L)	Au(30 nm)/G(1L)
$FWHM$	10.7	22.06
$\Delta\theta_{SPR}$	1.367	6.20
$S$ (°/RIU)	101.88	89.29
$DA$	0.887	0.29
$Q$	9.67	4.26
ref	This work	[11]

#### 4. Conclusion

In this work, the effect of different Au(30 nm)/BP-TMDs( $\text{MoS}_2$ ,  $\text{WS}_2$ ,  $\text{MoSe}_2$ ,  $\text{WSe}_2$ ) combinations and the number of their flakes on the spectral response of an SPR biosensor was investigated and presented. Moreover, a comparison was made between the structure of layer and the medium. The results indicate that the BP- $\text{WSe}_2$ (1L) on Au(30 nm) has the highest sensitivity, which is 101.88°/RIU. The results

also show that increasing the thickness of layers in the output has a direct effect on the sensor's efficiency and improves sensor performance.

#### References

- [1] Wu, L., et al., *Highly sensitive graphene biosensors based on surface plasmon resonance*. Optics express, 2010. 18(14): p. 14390-14400.
- [2] Sreekanth, K.V., et al., *Sensitivity enhanced biosensor using graphene-based one-dimensional photonic crystal*. Sensors and Actuators B: Chemical, 2013. 182: p. 424-428.
- [3] Komlev, A., R. Dyukin, and E. Shutova. *The method of controlling the thickness of the deposited film on the basis of the surface plasmon resonance effect*. in *Journal of Physics: Conference Series*. 2017. IOP Publishing.
- [4] Wang, T., Y. Zhu, and Q. Jiang, *Bandgap opening of bilayer graphene by dual doping from organic molecule and substrate*. The Journal of Physical Chemistry C, 2013. 117(24): p. 12873-12881.
- [5] Fuhrer, M.S. and J. Hone, *Measurement of mobility in dual-gated MoS<sub>2</sub> 2 transistors*. Nature nanotechnology, 2013. 8(3): p. 146-149.
- [6] Sorkin, V., et al., *Solid State Mater. Sci*, 2017. 42: p. 1-82.
- [7] Peng, Q., et al., *Electronic structures and enhanced optical properties of blue phosphorene/transition metal dichalcogenides van der Waals heterostructures*. Scientific reports, 2016. 6(1): p. 1-10.
- [8] Vahed, H. and C. Nadri, *Sensitivity enhancement of SPR optical biosensor based on Graphene-MoS<sub>2</sub> structure with nanocomposite layer*. Optical Materials, 2019. 88: p. 161-166.
- [9] Han, L., et al., *High-sensitivity goos-hänchen shifts sensor based on bluep-tmdcs-graphene heterostructure*. Sensors, 2020. 20(12): p. 3600.
- [10] Dai, X., et al., *Sensitivity enhancement of a surface plasmon resonance with tin selenide (SnSe) allotropes*. Sensors, 2019. 19(1): p. 173.
- [11] Maurya, J., Y. Prajapati, and R. Tripathi, *Effect of molybdenum disulfide layer on*

*surface plasmon resonance biosensor for the  
detection of bacteria. Silicon*, ۲۰۱۸. ۱۰(۳): p.

۲۴۵-۲۵۶.